

Appendix: Drill Results

Table 1: Pinion SB Composite Drill Results (Composites Ox/Tr 0.17g/t Au cog & Sx 0.50g/t Au cog)

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 0.5g/t Au COG	Including 1g/t Au COG	Including 2g/t Au COG
PC23-01	108.81	117.96	9.1	1.46	85.2	13.39	Oxide	7.62m @ 1.71g/t Au & 82.4% CN Rec	7.62m @ 1.71g/t Au & 82.4% CN Rec	4.57m @ 2.1g/t Au & 84.2% CN Rec
PC23-01	125.58	238.29	112.7	0.72	73.8	80.62	Oxide	24.38m @ 1.3g/t Au & 66.5% CN Rec 4.57m @ .55g/t Au & 68.5% CN Rec 36.58m @ .63g/t Au & 82.1% CN Rec 11.22m @ 1.29g/t Au & 57.8% CN Rec	21.34m @ 1.38g/t Au & 72.4% CN Rec 1.52m @ 1.34g/t Au & 66.4% CN Rec 6.71m @ 1.7g/t Au & 49.1% CN Rec	1.52m @ 2.62g/t Au & 46.6% CN Rec 1.22m @ 2.6g/t Au & 42.3% CN Rec
PC23-01	238.29	249.02	10.7	1.05	15.3	11.31	Sulphide		9.14m @ 1.11g/t Au & 16.7% CN Rec	
PC23-01	249.02	257.25	8.2	2.33	81.9	19.16	Oxide	8.23m @ 2.33g/t Au & 81.9% CN Rec	2.87m @ 5.75g/t Au & 91.3% CN Rec	1.65m @ 8.98g/t Au & 93.4% CN Rec
PR23-01	64.01	92.96	29.0	0.56	75.4	16.14	Oxide	18.29m @ .77g/t Au & 75.3% CN Rec	1.52m @ 1.56g/t Au & 72.4% CN Rec	
PR23-01	105.16	176.78	71.6	0.78	83.7	55.71	Oxide	38.1m @ 1.29g/t Au & 83.6% CN Rec 1.52m @ .56g/t Au & 80.6% CN Rec	1.52m @ 2.04g/t Au & 90.2% CN Rec 16.76m @ 1.79g/t Au & 78.8% CN Rec 3.05m @ 1.56g/t Au & 94.7% CN Rec	1.52m @ 2.04g/t Au & 90.2% CN Rec 1.52m @ 6.68g/t Au & 81.6% CN Rec
PR23-02	97.54	126.49	29.0	0.44	81.1	12.75	Oxide	12.19m @ .57g/t Au & 83.8% CN Rec 1.52m @ .76g/t Au & 1.3% CN Rec 1.52m @ .66g/t Au & 100.8% CN Rec	1.52m @ 1.04g/t Au & 89.4% CN Rec	
PR23-02	140.21	179.83	39.6	0.50	88.3	19.98	Oxide	16.76m @ .9g/t Au & 89.7% CN Rec	9.14m @ 1.1g/t Au & 91% CN Rec	1.52m @ 2.07g/t Au & 90.3% CN Rec

Criteria: Cut off grade Ox/Tr 0.17g/t Au & Sx 0.50g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m

Table 2: Dark Star Composite Drill Results (Composites Ox/Tr 0.17g/t Au cog & Sx 0.50g/t Au cog)

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 0.5g/t Au COG	Including 1g/t Au COG	Including 2g/t Au COG	Including 10g/t Au HG
DR23-01	106.68	109.73	3.0	1.17	95.0	3.58	Oxide	3.05m @ 1.17g/t Au & 95% CN Rec	1.52m @ 1.49g/t Au & 96.6% CN Rec		
DR23-01	124.97	126.49	1.5	0.20	89.1	0.31	Oxide				
DR23-01	131.06	132.59	1.5	0.26	91.6	0.40	Oxide				
DR23-01	140.21	144.78	4.6	0.44	95.2	2.01	Oxide	1.52m @ .61g/t Au & 91.4% CN Rec			
DR23-01	150.88	152.40	1.5	0.43	92.4	0.66	Oxide				
DR23-01	182.88	219.46	36.6	3.53	82.7	129.19	Oxide	36.58m @ 3.53g/t Au & 82.7% CN Rec	36.58m @ 3.53g/t Au & 82.7% CN Rec	3.05m @ 3g/t Au & 97.4% CN Rec 19.81m @ 5.23g/t Au & 81.5% CN Rec	3.05m @ 11.83g/t Au & 87.2% CN Rec
DR23-01	219.46	224.03	4.6	2.48	22.8	11.34	Sulphide	4.57m @ 2.48g/t Au & 22.8% CN Rec	4.57m @ 2.48g/t Au & 22.8% CN Rec	4.57m @ 2.48g/t Au & 22.8% CN Rec	
DR23-02	18.29	30.48	12.2	0.66	82.0	8.10	Oxide	4.57m @ 1.27g/t Au & 84.5% CN Rec	3.05m @ 1.53g/t Au & 81.9% CN Rec		
DR23-02	41.15	204.22	163.1	2.20	82.9	358.59	Oxide	158.5m @ 2.26g/t Au & 82.9% CN Rec	19.81m @ 2.06g/t Au & 88.2% CN Rec 123.44m @ 2.48g/t Au & 82% CN Rec	18.29m @ 2.08g/t Au & 88.2% CN Rec 9.14m @ 2.17g/t Au & 82.2% CN Rec 30.48m @ 3.97g/t Au & 77.6% CN Rec 27.43m @ 2.56g/t Au & 87.1% CN Rec 6.1m @ 6.88g/t Au & 68.2% CN Rec	1.52m @ 12.33g/t Au & 45.6% CN Rec
DR23-02	204.22	214.88	10.7	11.47	28.1	122.40	Sulphide	10.67m @ 11.47g/t Au & 28.1% CN Rec	10.67m @ 11.47g/t Au & 28.1% CN Rec	10.67m @ 11.47g/t Au & 28.1% CN Rec	7.62m @ 14.53g/t Au & 26.2% CN Rec
DR23-02	214.88	254.51	39.6	3.03	74.0	120.04	Oxide	32m @ 3.7g/t Au & 76% CN Rec	30.48m @ 3.85g/t Au & 77.4% CN Rec	30.48m @ 3.85g/t Au & 77.4% CN Rec	1.52m @ 14g/t Au & 15.8% CN Rec
DR23-02	260.60	262.13	1.5	0.23	64.1	0.36	Oxide				
DSC23-01	215.19	216.71	1.5	0.20	99.0	0.31	Oxide				
DSC23-01	256.49	268.99	12.5	1.66	22.6	20.71	Sulphide	10.82m @ 1.82g/t Au & 22.6% CN Rec	1.52m @ 2.17g/t Au & 30.4% CN Rec 3.05m @ 3.72g/t Au & 25.4% CN Rec		
DSC23-02	43.89	49.53	5.6	0.32	70.1	1.82	Oxide	1.52m @ .55g/t Au & 47.3% CN Rec			
DSC23-02	64.01	65.53	1.5	0.17	86.7	0.26	Oxide				
DSC23-02	97.84	112.78	14.9	0.65	86.9	9.78	Oxide	6.25m @ 1.27g/t Au & 85.6% CN Rec	1.22m @ 4.29g/t Au & 90% CN Rec	1.22m @ 4.29g/t Au & 90% CN Rec	
DSC23-02	130.15	143.10	13.0	0.30	94.5	3.85	Oxide	1.37m @ .76g/t Au & 99.1% CN Rec			
DSC23-02	162.31	250.39	88.1	2.50	90.8	220.20	Oxide	69.13m @ 3.14g/t Au & 89.5% CN Rec	55.17m @ 3.64g/t Au & 90% CN Rec	30.48m @ 5.69g/t Au & 92.8% CN Rec	2.13m @ 11.96g/t Au & 88% CN Rec 1.37m @ 13.6g/t Au & 91.5% CN Rec

Criteria: Cut off grade Ox/Tr 0.17g/t Au & Sx 0.50g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m

Table 3: South Railroad Drill Collars

Hole number	Target	Hole type	Grid	Easting m	Northing m	Elevation m	az_utm	dip	Depth (m)
DR23-01	Dark Star	RC	NAD27 / UTM zone 11N	588164.7	4480033.83	2009.1	270.0	-75.0	292.6
DR23-02	Dark Star	RC	NAD27 / UTM zone 11N	588140.9	4480160.80	2024.4	270.0	-75.0	262.1
DSC23-01	Dark Star	DD	NAD27 / UTM zone 11N	588120.3	4480264.29	2024.6	270.0	-90.0	819.3
DSC23-02	Dark Star	DD	NAD27 / UTM zone 11N	588122.3	4480192.28	2030.9	270.0	-75.0	311.8
PC23-01	Pinion	DD	NAD27 / UTM zone 11N	585305.1	4478648.90	2101.5	270.0	-60.0	297.5
PR23-01	Pinion	RC	NAD27 / UTM zone 11N	585215.3	4478694.68	2088.8	90.0	-75.0	265.2
PR23-02	Pinion	RC	NAD27 / UTM zone 11N	585215.9	4478695.21	2091.3	0.0	-90.0	259.1