

## Appendix: Drill Results

Table 1: North Bullion Composite Drill Results (Composites Ox/Tr 0.17g/t Au cog & Sx 0.5g/t Au cog)

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 1g/t Au COG	Including 2g/t Au COG	Including 10g/t Au HG
RR23-01	137.16	140.21	3.0	1.04	6.7	3.17	Sulphide	1.52m @ 1.21g/t Au & 4.1% CN Rec		
RR23-01	294.13	297.18	3.0	0.68	3.6	2.08	Sulphide			
RR23-01	310.90	312.42	1.5	0.57	5.3	0.87	Sulphide			
RR23-01	324.61	355.09	30.5	1.30	4.7	39.55	Sulphide	22.86m @ 1.58g/t Au & 5% CN Rec	6.1m @ 2.13g/t Au & 5% CN Rec	1.52m @ 2.8g/t Au & 8.2% CN Rec
RR23-01	370.33	371.86	1.5	0.86	2.3	1.31	Sulphide			
RR23-04	163.07	187.45	24.4	2.37	3.3	57.86	Sulphide	15.24m @ 3.46g/t Au & 4.5% CN Rec	15.24m @ 3.46g/t Au & 4.5% CN Rec	
RR23-04	259.08	321.56	62.5	1.07	3.9	66.90	Sulphide	9.14m @ 1.54g/t Au & 5.2% CN Rec 6.1m @ 2.59g/t Au & 4.1% CN Rec 15.24m @ 1.15g/t Au & 3.6% CN Rec	6.1m @ 2.59g/t Au & 4.1% CN Rec	
RR23-04	329.18	353.57	24.4	0.60	1.9	14.75	Sulphide	1.52m @ 1.03g/t Au & 1% CN Rec		
RR23-05	138.68	141.73	3.0	1.16	1.3	3.54	Sulphide	1.52m @ 1.56g/t Au & 1.3% CN Rec		
RR23-05	150.88	202.69	51.8	3.24	3.0	168.06	Sulphide	48.77m @ 3.4g/t Au & 3.1% CN Rec	44.2m @ 3.6g/t Au & 2.9% CN Rec	
RR23-06	173.74	198.12	24.4	2.00	1.2	48.82	Sulphide	18.29m @ 2.44g/t Au & 1.2% CN Rec	16.76m @ 2.56g/t Au & 1.2% CN Rec	
RR23-08	286.51	297.79	11.3	0.51	1.6	5.73	Sulphide			
RR23-09	207.57	250.24	42.7	3.96	8.7	168.90	Sulphide	42.67m @ 3.96g/t Au & 8.7% CN Rec	20.73m @ 3g/t Au & 9.7% CN Rec 13.72m @ 7.09g/t Au & 7.4% CN Rec	3.05m @ 21.07g/t Au & 11.2% CN Rec
RR23-09	311.51	377.04	65.5	1.15	3.2	75.61	Sulphide	46.63m @ 1.33g/t Au & 3.6% CN Rec 1.52m @ 1.76g/t Au & .6% CN Rec	1.52m @ 2g/t Au & 5.5% CN Rec 1.52m @ 2.08g/t Au & 4.3% CN Rec	
RR23-10	92.96	96.01	3.0	0.59	4.2	1.80	Sulphide			
RR23-10	292.61	301.75	9.1	0.57	1.0	5.20	Sulphide			
RR23-10	332.23	338.33	6.1	0.64	1.8	3.92	Sulphide			
RR23-10	361.19	362.71	1.5	0.52	9.6	0.80	Sulphide			
RR23-12	323.09	344.42	21.3	2.55	0.8	54.46	Sulphide	16.76m @ 3.09g/t Au & .8% CN Rec	13.72m @ 3.5g/t Au & .9% CN Rec	
RR23-12	355.09	382.52	27.4	0.81	2.9	22.23	Sulphide	7.62m @ 1.17g/t Au & 1.3% CN Rec 4.57m @ 1.66g/t Au & 7.1% CN Rec 76.2m @ 2.16g/t Au & 1.5% CN Rec	1.52m @ 2.3g/t Au & 7% CN Rec	
RR23-13	275.84	381.00	105.2	1.78	1.7	187.70	Sulphide	6.1m @ 1.65g/t Au & 2.1% CN Rec	54.86m @ 2.54g/t Au & 1.7% CN Rec 3.05m @ 2.42g/t Au & 2.5% CN Rec 1.07m @ 3.19g/t Au & 3.4% CN Rec 2.13m @ 3.57g/t Au & .8% CN Rec	
RR23-14	265.48	281.64	16.2	1.24	1.4	19.98	Sulphide	11.28m @ 1.5g/t Au & 1.4% CN Rec		
RR23-14	299.44	305.11	5.7	1.09	0.8	6.16	Sulphide	2.44m @ 1.48g/t Au & .9% CN Rec		
RR23-14	317.91	320.50	2.6	0.59	1.7	1.52	Sulphide			
RR23-14	327.48	379.93	52.5	1.17	2.2	61.20	Sulphide	10.67m @ 2.77g/t Au & 2.3% CN Rec 9.75m @ 1.35g/t Au & 1.4% CN Rec	5.88m @ 3.85g/t Au & 3% CN Rec 3.66m @ 2.15g/t Au & 1.8% CN Rec	
RRC23-01	191.11	194.16	3.0	1.14	4.0	3.46	Sulphide	3.05m @ 1.14g/t Au & 4% CN Rec		
RRC23-01	232.26	256.03	23.8	1.51	7.9	35.88	Sulphide	17.37m @ 1.86g/t Au & 6.5% CN Rec	7.92m @ 2.5g/t Au & 6.6% CN Rec	
RRC23-02	198.58	204.83	6.2	0.64	0.8	4.01	Sulphide			
RRC23-02	220.07	223.11	3.0	0.87	5.3	2.65	Sulphide	1.52m @ 1.21g/t Au & 5% CN Rec		
RRC23-02	232.26	249.33	17.1	2.27	4.8	38.79	Sulphide	15.54m @ 2.47g/t Au & 4.8% CN Rec	9.45m @ 3.64g/t Au & 6.2% CN Rec	
RRC23-02	266.40	267.92	1.5	0.68	0.7	1.03	Sulphide			
RRC23-02	277.98	279.50	1.5	0.60	0.8	0.92	Sulphide			
RRC23-02	329.79	335.28	5.5	0.76	1.4	4.15	Sulphide	1.22m @ 1.24g/t Au & 2.4% CN Rec		
RRC23-02	346.25	355.70	9.4	4.30	2.1	40.62	Sulphide	9.45m @ 4.3g/t Au & 2.1% CN Rec	9.45m @ 4.3g/t Au & 2.1% CN Rec	1.83m @ 11.6g/t Au & 6.6% CN Rec
RRC23-02	361.80	369.42	7.6	0.82	1.5	6.26	Sulphide			
RRC23-02	377.04	385.27	8.2	0.82	0.7	6.73	Sulphide			

Criteria: Cut off grade Ox/Tr 0.17g/t Au & Sx 0.5g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m

Ox= Oxide, TR= Transition, SX= Sulphide. True width of intercepts is uncertain but estimated to range between 40-85% of core length.

**Table 2: POD Regional Program Composite Drill Results**

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	Ag (g/t)	Including
RRC23-04	84.28	85.95	1.7	0.01	487.0	
RRC23-04	155.30	157.43	2.1	0.01	533.9	0.6m @ 1511g/t Ag
RRC23-04	212.90	213.67	0.8	0.01	163.0	
RRC23-04	226.92	233.32	6.4	0.02	95.0	1.2m @ 349g/t Ag
RRC23-04	258.32	261.98	3.7	0.06	477.0	1.5m @ 1101g/t Ag

Criteria: Cut off grade 41.7g/t Ag, minimum length 1.5m, maximum consecutive internal waste 6m, if Ag grade x length > 62.5 the composite will be added. True width of intercepts are uncertain.

**Table 3: Jasperoid Wash Regional Program Composite Drill Results**

HOLE-ID	From (m)	To (m)	Core Length (m)	Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 0.5g/t Au COG	Including 1g/t Au COG
JW23-03	132.59	134.11	1.5	0.17	74.7	0.27	Oxide		
JW23-04	225.55	227.08	1.5	0.20	40.8	0.30	Oxide		
JWC23-01	0.00	17.68	17.7	0.53	91.0	9.37	Oxide	10.67m @ .73g/t Au & 96.5% CN Rec	1.52m @ 1.99g/t Au & 97% CN Rec
JWC23-01	38.28	42.73	4.4	0.35	59.1	1.57	Oxide		
JWC23-01	127.04	128.38	1.3	0.73	33.0	0.98	Sulphide		
JWC23-01	128.38	153.31	24.9	0.32	84.9	8.00	Oxide	1.31m @ 1.15g/t Au & 70.4% CN Rec	1.31m @ 1.15g/t Au & 70.4% CN Rec
JWC23-02	3.66	47.85	44.2	0.85	76.6	37.56	Oxide	42.67m @ .86g/t Au & 76% CN Rec	2.74m @ 1.46g/t Au & 96.6% CN Rec 18.29m @ 1.21g/t Au & 59% CN Rec
JWC23-02	117.35	118.87	1.5	0.27	93.3	0.41	Oxide		
JWC23-03	21.95	31.91	10.0	0.24	81.8	2.37	Oxide		
JWC23-03	47.24	56.78	9.5	0.24	88.1	2.26	Oxide		
JWC23-03	63.09	78.64	15.5	0.27	81.4	4.24	Oxide		
JWC23-03	92.66	94.18	1.5	0.19	94.7	0.29	Oxide		
JWC23-04	41.45	63.40	21.9	0.23	80.3	5.00	Oxide	1.52m @ .58g/t Au & 82.5% CN Rec	
JWC23-04	72.85	83.52	10.7	0.20	75.0	2.16	Oxide		
JWC23-04	89.67	92.05	2.4	0.20	79.2	0.48	Oxide		
JWC23-05	5.09	6.71	1.6	0.24	84.4	0.38	Oxide		
JWC23-05	12.80	28.04	15.2	0.19	79.3	2.86	Oxide		
JWC23-05	38.71	40.23	1.5	0.17	76.0	0.26	Oxide		
JWC23-05	49.07	52.12	3.0	0.30	82.0	0.91	Oxide		
JWC23-05	63.09	65.47	2.4	0.19	84.4	0.46	Oxide		
JWC23-05	70.10	71.63	1.5	0.19	83.3	0.29	Oxide		
JWC23-05	85.34	92.05	6.7	0.37	73.4	2.50	Oxide	2.26m @ .6g/t Au & 72.1% CN Rec	

Criteria: Cut off grade Ox/Tr 0.17g/t Au & Sx 0.5g/t Au, minimum length 1.5m, maximum consecutive internal waste 6m

Ox= Oxide, TR= Transition, SX= Sulphide. True width of intercepts is uncertain but estimated to range between 30-85% of core length.

**Table 4: South Railroad Drill Hole Collars**

Hole number	Target	Hole type	Grid	Easting m	Northing m	Elevation m	az_utm	dip	Depth (m)
JW23-01	Jasperoid Wash	RC	NAD27 / UTM zone 11N	585673.9	4472391.86	2310.4	30.0	-45.0	97.5
JW23-02	Jasperoid Wash	RC	NAD27 / UTM zone 11N	585363.6	4472432.08	2328.9	30.0	-60.0	262.1
JW23-03	Jasperoid Wash	RC	NAD27 / UTM zone 11N	585093.7	4472480.24	2325.5	30.0	-60.0	298.7
JW23-04	Jasperoid Wash	RC	NAD27 / UTM zone 11N	584802.6	4472044.61	2188.2	60.0	-50.0	243.8
JWC23-01	Jasperoid Wash	DD	NAD27 / UTM zone 11N	584849.3	4473494.46	2356.1	0.0	-60.0	162.2
JWC23-02	Jasperoid Wash	DD	NAD27 / UTM zone 11N	584847.6	4473502.32	2356.0	180.0	-60.0	118.9
JWC23-03	Jasperoid Wash	DD	NAD27 / UTM zone 11N	585167.3	4473160.95	2462.8	70.0	-50.0	94.2
JWC23-04	Jasperoid Wash	DD	NAD27 / UTM zone 11N	585068.5	4473181.95	2427.3	70.0	-50.0	92.0
JWC23-05	Jasperoid Wash	DD	NAD27 / UTM zone 11N	584949.1	4473165.68	2396.1	70.0	-50.0	92.0
RR23-01	North Bullion	RC	NAD27 / UTM zone 11N	584864.3	4488438.04	2064.3	220.0	-70.0	426.7
RR23-02	North Bullion	RC	NAD27 / UTM zone 11N	584945.4	4488230.79	2045.3	220.0	-70.0	408.4
RR23-03	North Bullion	RC/DD	NAD27 / UTM zone 11N	584954.7	4488800.08	1989.6	180.0	-83.0	198.1
RR23-04	North Bullion	RC	NAD27 / UTM zone 11N	584870.5	4488604.17	2028.5	160.0	-75.0	353.6
RR23-05	North Bullion	RC	NAD27 / UTM zone 11N	584871.7	4488605.53	2028.5	125.0	-70.0	243.8
RR23-06	North Bullion	RC	NAD27 / UTM zone 11N	584863.4	4488608.55	2028.5	35.0	-78.0	249.9
RR23-07	North Bullion	RC/DD	NAD27 / UTM zone 11N	584817.1	4488931.71	1993.5	225.0	-70.0	219.5
RR23-08	North Bullion	RC/DD	NAD27 / UTM zone 11N	584784.9	4488795.27	2002.0	210.0	-70.0	326.3
RR23-09	North Bullion	RC/DD	NAD27 / UTM zone 11N	585073.5	4488799.80	1981.4	238.0	-66.0	381.6
RR23-10	North Bullion	RC	NAD27 / UTM zone 11N	584806.0	4488276.42	2057.1	220.0	-70.0	365.8
RR23-11	POD	RC	NAD27 / UTM zone 11N	583754.3	4487685.30	2233.4	210.0	-75.0	365.8
RR23-12	North Bullion	RC	NAD27 / UTM zone 11N	584953.0	4488807.28	1989.6	315.0	-87.0	426.7
RR23-13	North Bullion	RC	NAD27 / UTM zone 11N	584953.3	4488805.48	1989.7	248.0	-83.0	419.1
RR23-14	North Bullion	RC/DD	NAD27 / UTM zone 11N	584953.9	4488801.38	1989.0	180.0	-83.0	420.0
RR23-15	North Bullion	RC	NAD27 / UTM zone 11N	583779.5	4488645.29	2116.6	0.0	-90.0	542.5
RRC23-01	North Bullion	DD	NAD27 / UTM zone 11N	585075.5	4488804.10	1981.4	230.0	-71.0	257.3
RRC23-02	North Bullion	DD	NAD27 / UTM zone 11N	585066.2	4488855.24	1976.5	220.0	-70.0	412.1
RRC23-03	North Bullion	DD	NAD27 / UTM zone 11N	584946.4	4488801.55	1989.5	253.0	-75.0	93.9
RRC23-04	POD	DD	NAD27 / UTM zone 11N	583792.5	4487709.66	2219.1	210.0	-75.0	332.1